

Motosel Full Synthetic Automatic Transmission Fluid is

formulated to meet the stringent specifications of the ZF Group including: all ZF 3 & 4 speed transmission, ZF 8 & 9 speed transmissions, and where ZF TE-ML 05L, ZF TE-ML 09, ZF TE-ML 11A, 11B, and ZF TE-ML 21L are recommended. It provides extreme protection including additional oxidation control, excellent low temperature and superior shear stability performance in modern passenger car, flex-fuel vehicle, hybrid, truck, and sport utility vehicle transmissions. It is also suitable for use in automatic transmissions calling for VAG G-080-162 • BMW 8322 2152428 / 2289720(ATF3+) • JAGUAR 02JDE 26444 • LAND ROVER LR023288 • CHRYSLER 68157995AA • JEEP • FIAT 9.55550-AV5 and many other American, Asian and European OEM's performance standards where a premium full synthetic ATF is recommended.

Benefits and Applications

- Full synthetic maximum corrosion, wear, and rust protection
- Outstanding low temperature flow properties
- Enhanced friction additives and oxidation stability for longer fluid life
- Smooth shifting and reduce shudder performance
- High compatibility suitable for use in most applications

Suitable for:

ZF Group including: all ZF 3 & 4 speed transmission, ZF 8 & 9 speed transmissions, and where ZF TE-ML 05L, ZF TE-ML09, ZF TE-ML 11A, 11B, and ZF TE-ML 21L



#4013M / 1Qt #M-0175 / 5Gal #M-0158 / 22.7L #M-0176 / 55Gal #M-0177 / Bulk

TYPICAL CHARACTERISTICS - 8&9 SPEED

SAE GRADE	TEST METHOD	8&9 SPEED
Colour	Visual	Red
Viscosity @ 100°C, cSt	ASTMD 445	7.0
Viscosity @ 40°C, cSt	ASTMD 445	32.9
Viscosity Index	ASTMD 2270	180
Pour Point, °C/°F	ASTMD 97	-51/-59.8
Flash Point, COC °C/°F	ASTMD 92	204 / 399.2
API Gravity	ASTMD 1298	32.6
Brookfield Vis.cP @ -40°C	ASTMD 2983	16200

Typical test data are average values only. Minor variations, which do not affect performance, may occur. You should consult your owner's manual to verify proper fluid recommendation for your particular vehicle.

HANDLING AND SAFETY INFORMATION - Refer to MOTOSEL (SDS) Safety Data Sheets for proper handling and safety information. Use the same care and handling as for any petroleum product. Nothing herein shall be deemed to constitute a warranty, express or implied, that said information or data are correct or that the products described are merchantable or fit for a particular purpose, or that said information, data or products can be used without infringing patents of third parties.

